



Aerosol and Touch up Lacquer (Gloss)

Description

One component acrylic lacquer which can be applied over most suitably prepared basepaints. Any gloss surfaces must be lightly rubbed down with 1200 before application. Easy application, fast drying, non-yellowing, easy to polish.

Drying Times

(air drying at 20°C)

Number of coats: 2 – 3

Dust free 3 – 5 mins

Tack free 15-20 mins

Through drying: 6 hours

Interval between coats: 10 mins

Polishing: after 24 hours at room temperature. The complete hardening occurs in the following 3-4 days.

NOTES

Aerosol and touch up lacquer is not petrol proof. It is suitable for all motorbike parts, except for the tank. For petrol proof lacquer, please see our 2K gloss Isocyanate free lacquer for spray gun application.

The painted substrate must not be exposed to severe conditions in the first days after the painting. Until fully cured, strong humidity condensations, like dew and frost and contact with aggressive agents like smog, detergents and salt on the roads must be avoided.